



XL FLOORING

**Tile
& Done**
FLOORING

SPECIFICATIONS

Item	Spec	Spec
Width	12" (305 mm)	
Length	24" (609.5 mm)	
Thickness	5.0 mm (3/16")	
Wear Layer Thickness	0.5 mm (20mil)	
Profile	Non-beveled	
Sq.Ft. per Carton	20 sq.ft (1.86 sq.m)	
Planks per Carton	10	
Weight per Carton	36.4 lbs. (16.5 kg)	
Cartons per Pallet	60	
Sq.Ft. per Pallet	1200 sq.ft (111.48 sq.m)	
Weight per Pallet	2184 lbs. (990.65 kg)	
Type & Composition	PVC Laminate Floor Covering	
Application	Residential & Commercial	
Surface Treatment	Duracoat Polyurethane, anti-microbial with micro-ceramic beads	
Backing	Sound Absorbing XL Backing	
Warranty	15 Year Limited Commercial Lifetime Limited Residential	



XL FLOORING

Product tests carried out by independent testing labs.

- Intertek, Cortland NY.
- Testing Services Inc, Dalton Georgia



TEST RESULTS

Item	Spec/Test	Result			
Dimensional Stability	ASTM F2199	.0038% inch/foot			
Sound Absorbtion	IIC RATING/STC RATING	54/61			
Use with Underfloor Radiant Heating	Recommended				
Floorscore Testing	Floorscore Certified				
Emmissions German Dibit Results	TVOC after 3 days	0.095 parts/million			
	TVOC after 28 days	0.005 parts/million			
	SVOC after 28 days	0.005 parts/million			
	Phenol after 28 days	0.000 parts/million			
Critical Radiant Flux	ASTM E648-06 Mekol Burner Test	0.99 watts/cm ² Pass			
Light Fastness 300 HRS.	ASTM F1515	6.0			
Heat Stability	ASTM 1514	4.3			
Slip Resistance	AS 4586 (CSIRO): Classification Walking Angle ADA	R=10 (meets commercial standard} 16° exceeds ADA requirement			
Abrasian Resistance	ASTM D3884	0.003% @ 1000 cycles			
Stain & Chemical Resistance	KSM 3802 - 24 Hour Exposure	95% ethyl Alcohol	0	Tea	0
		Cement Paste	0	Ketchup	0
		10% ammonium hydroxide	0	Nitric Acid	1
		Kerosene	0	Sulfuric Acid 95%	1
		Sesame Oil	0	Acetone	2
		Soy Sauce	0	Nail Polish Remover	2
		Soy Bean Oil	0	Methylene Chloride	2
		Lubricant	0		
		Coffee	0		
		Deflection	ASTM F1304	55.29 mm	
Smoke Density - Flaming	ASTM E662	280 (Corrected to Max Density)			
Smoke Density - Non-Flaming	ASTM E662	417 (Corrected to Max Density)			
Short Term Indentation	ASTM F1914	0.008"			
Static Load 1,000 PSI	ASTM F970	0.005° of residual indentation			
Static Coefficient of Friction	ASTM D2047 ASTM C1028	Dry: 0.60			
		Dry: 0.7144			
		Wet: 0.8900			
Rolling Chair 25,000 hours	ASTM F2753	Negligible Disturbance			