

EZ LAY®

F L O O R I N G

A division of XL Flooring Co. Ltd.

SPECIFICATIONS

Planchers de luxe en vinyle
ezgripmce
Luxury Vinyl Flooring

Item	Spec	Spec
Width	7" (178 mm)	
Length	48" (1219 mm)	
Thickness	5.0 mm (3/16")	
Wear Layer Thickness	0.5 mm (20mil)	
Surface Profile	Registered Emboss	
Sq.Ft. per Carton	23.3 sq.ft (2.16 sq.m)	
Planks per Carton	10	
Weight per Carton	37.0 lbs. (16.78 kg)	
Cartons per Pallet	60	
Sq.Ft. per Pallet	1398 sq.ft (129.87 sq.m)	
Weight per Pallet	2,220 lbs. (1007.00 kg)	
Type & Composition	PVC Laminate Floor Covering	
Application	Residential & Commercial	
Surface Treatment	Duracoat Polyurethane, anti-microbial, embedded with micro-ceramic beads	
Visual Pattern Repeat	Approx. every 1,200mm (39.37in)	Approx. 1 plank in every 8 cartons
Backing	Sound Absorbing IXPE Sound Backing	
Warranty	15 Year Limited Commercial Lifetime Limited Residential	

TEST RESULTS

Product testing carried out by independant testing labs.

STANDARD	TEST ITEM	TEST METHOD	REQUIREMENT	PERFORMANCE
ASTM F1700	Dimensions	ASTM F2421	± 0.016 in./lin. ft	Meets
	Squareness	ASTM F2421	Max 0.010 in. (0.25mm)	Meets
	Overall Thickness	ASTM F386	As specified ± 0.005 in. (0.13mm)	Meets
	Wear Layer Thickness	ASTM F410	Max. 0.20 in. (as commercial)	Meets
	Dimensional Stability	ASTM F2199	Max. 0.020 in./lin. ft	Meets
	Flexibility	ASTM F137	1-in. Mandrel no crack or break	Meets
	Resistance to Chemicals	ASTM F925	No more than a slight change	Meets
	Resistance to Light	ASTM F1515	ΔE < 8 ave MAX	Meets
	Resistance to Heat	ASTM F1514	ΔE < 8 ave MAX	Meets
Other Testing	Static Load Limit	ASTM F970	Min 0.005 in. or less @ 250 psi	Meets
	Fire Resistance - CRF	ASTM E648	Class 1 (0.45 watts/cm ² or more)	Meets
	Smoke Density	ASTM E662	450 or less	Meets
	IIC (Impact Insulation Class)	ASTM E492	With no drop ceiling	IIC 55
	IIC (Impact Insulation Class)	ASTM E492	With drop ceiling	IIC 70
	SCOF	ASTM D2047	More than 0.06	Meets
	Indoor Air Quality	CDPH/EHLB V1.2 - 2017	Low VOC	FloorScore Certified

CERTIFICATIONS

